

# Peltron®

<b>Product Name</b>	C-4408
<b>Product Category</b>	Anti-Static Coating
<b>Usage</b>	Display, Functional Films
<b>Function</b>	Antistatic

Item	Condition	Unit	Typical Value
<b>General Items</b>			
<b>Applicable materials</b>	-	-	Transparent substrate
<b>Conductive fillers</b>	-	-	Antimony doped tin oxide
<b>Liquid properties</b>			
<b>Solid content</b>	-	%	34
<b>Applicable diluents</b>	-	-	MEK
<b>Drying Properties</b>			
Coating conditions : solid content 8.5wt%/bar coater #5/Substrate : PET film 125µm			
Drying conditions : room temperature 3min→60°Cx20min			
<b>Surface Resistance</b>	Resistance Rate Meter HIRESTA	Ω/sq.	1.70E+06
<b>Total light transmission</b>	turbidity meter NDH2000	%	89.0
<b>Haze</b>	turbidity meter NDH2000	%	7.3

The above values are typical and not specification



**PELNOX, LTD.**

Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan  
TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan  
TEL : 81-463-86-8001 FAX : 81-463-86-8022