

## Peltron®

<b>Product Name</b>	R-5039
<b>Product Category</b>	Protective Paste for Chip Component
<b>Usage</b>	Car Electro Devices, Ceramic Capacitors, Small Components Electrode
<b>Function</b>	One Component, Moisture Resistant

### As supplied

Item	Condition	Unit	Typical Value
Viscosity	BrookField HB type viscometer, SC4-14, 50rpm 25°C	Pa·s	130

**Standard Curing Condition**    **180°C - 30 minutes or 210°C - 10 minutes**

### As cured

Item	Condition	Unit	Typical Value
Volume Resistivity	-	Ω·cm	$1.5 \times 10^{15}$

The above values are typical and not specification



## PELNOX, LTD.

Tokyo Sales Office    3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan  
TEL : 81-3-5645-3782    FAX : 81-3-5645-3784

R&D Center    8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan  
TEL : 81-463-86-8001    FAX : 81-463-86-8022

