

## Peltron®

|                         |   |
|-------------------------|---|
| <b>Product Name</b>     | R-5040  |
| <b>Product Category</b> | Protective Paste for Chip Component                                 |
| <b>Usage</b>            | Car Electro Devices, Ceramic Capacitors, Small Components Electrode |
| <b>Function</b>         | One Component, Moisture Resistant                                   |

### As supplied

| Item      | Condition   | Unit | Typical Value |
|-----------|---|------|---------------|
| Viscosity | BrookField HB type viscometer, SC4-14, 50rpm 25°C | Pa·s | 120           |

**Standard Curing Condition**    **180°C - 30 minutes or 210°C - 10 minutes**

### As cured

| Item               | Condition | Unit | Typical Value        |
|--------------------|-----------|------|----------------------|
| Volume Resistivity | -         | Ω·cm | $1.5 \times 10^{15}$ |

The above values are typical and not specification



## PELNOX, LTD.

Tokyo Sales Office    3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan  
TEL : 81-3-5645-3782    FAX : 81-3-5645-3784

R&D Center    8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan  
TEL : 81-463-86-8001    FAX : 81-463-86-8022

