

Pelnox®

Product Name	WE-3020
Product Category	One Component Type Resin
Usage	Binders
Function	

As supplied

(Typical Value)

Item	Condition	Unit	WE-3020
Appearance	visual	—	Black-brown liquid
Specific Gravity	25℃	—	1.20
Viscosity	25℃	mPa·s	2,800
Gel Time	150℃ hot plate	second	120

Standard Curing Condition 150℃ x 30 minutes

As cured

Item	Condition	Unit	Typical Value
Glass Transition Temperature	DSC	℃	110

The above values are typical and not specification



PELNOX, LTD.

Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan
TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan
TEL : 81-463-86-8001 FAX : 81-463-86-8022