

Peltron®

Product Name	XJK-0390A
Product Category	Electrically conductive Paste for Electrodes
Usage	Car Electro Devices, Ceramic Capacitors, Small Components Electrode
Function	One Component, Heat Resistant, Heat Cycle Resistant, Good Plating Property

Item	Condition	Unit	Typical Value
Liquid Feature			
Viscosity	Brookfield HBT / 50rpm @25°C	Pa·s	30
Best Coating Method	—	—	Dip coating
Storage Stability	Unopen / Frozen at -	—	3 months
Cured Film Feature			
Color	visual	—	Silver grey
Recommended Curing Condition	Heat air circulation oven	—	200°C x 30 minutes
Volume Resistivity	Curing for 30 minutes at 200°C	Ω·cm	1.4×10^{-4}

The above values are typical and not specification



PELNOX, LTD.

Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan
TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan
TEL : 81-463-86-8001 FAX : 81-463-86-8022