

Peltron®

Product Name	K-3330
Product Category	Conductive Paste for Circuit/Electrode
Use	General Modules, Touch Panel, Solar Battery
Function	One Component Type, Flexible, Fine Line Printing, Bending Resistant

Item	Condition	Unit	Typical Value
Liquid Feature			
Viscosity	Brook Field HBT / #7 / @25°C	Pa·s	245
Available Print Line Width	Screen Printing / 500~600mesh	μm	≥60
Diluent	–	–	Pelnox's Diluent #713
Storage Stability	Unopen / storage at 0~10°C	–	Three months
Cured Film Feature			
Color	visual	–	Grey black
Recommended Curing Condition	Heat air circulation oven	–	130°C x 30 minutes
Volume Resistivity	curing for 30minutes at 130°C	Ω·cm	5.0 x 10 ⁻⁵
Characteristics	Standard type conductive paste for capacitive touch panel circuitry. Available circuitry of 30μm line width by screen printing.		

The above values are reference and not specification.



PELNOX, LTD.

Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan
 TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan
 TEL : 81-463-86-8001 FAX : 81-463-86-8022