

Pelnox®

Product Name	ME-274/HV-134
Product Category	Potting Resin for Seiconductors, Resin for Car Electro Devices & Sensors
Usage	Semiconductor Modules, Car Electro Devices, Sensors
Function	Heat Resistant, Flame Resistant, Heat Cycle Resistant, Humidity Resistant

As supplied (Typical Value)

Item	Condition	Unit	ME-274	HV-134
Appearance	visual	–	Black liquid	Grey white liquid
Specific Gravity	25°C	–	1.85	1.76
Viscosity	25°C	mPa·s	16,750	5,000
Mixing Ratio	parts by weight		100/100	
Pot Life	25°C, time up to double viscosity	hour	8	
Gel Time	100°C, 140°C 40g	minute	40, 7	
Mixed Viscosity	25°C	mPa·s	6,500	

Standard Curing Condition **185°C x 1 hour**

As cured

項目	条件	単位	代表値
Specific Gravity	Buoyancy method 25°C		1.83
Hardness	JIS K-7215 25°C	Shore D	93
Heat Distortion Temperature	JIS K-7191-3	°C	190
Glass Transition Temperature	TMA	°C	185
Coefficient of Thermal Expansion	below Tg	10 ⁻⁵ /°C	2.1
	above Tg	10 ⁻⁵ /°C	7.1
Flexural Strength	JIS K-6911	MPa	110
Flexural Modulus	JIS K-6911	MPa	9,000
Tensile Strength	JIS K-6911	MPa	77
Shear Adhesive Strength	JIS K-6850 Al-Al	MPa	10
	JIS K-6850 Cu-Cu	MPa	6
Shrinkage		%	0.50
Thermal Conductivity	Rapid thermal conductivity meter	W/mk	0.50
Specific Heat	JIS K-7123 -25°C	J/g·deg	0.799
	25°C		0.902
	50°C		0.936
	100°C		1.050
	150°C		1.137
	200°C		1.250
Breakdown Voltage	JIS K-2110 25°C	kV/mm	17
	100°C		18
	150°C		18
Volume Resistivity	JIS K 6911 25°C	Ω-cm	6.4 x 10 ¹⁶
	JIS K 6911 boil for 2hrs	Ω-cm	1.2 x 10 ¹⁶
Dielectric Constant	JIS K-6911 1KHz		3.8
	1MHz		3.7
Dielectric Loss Tangent	JIS K-6911 1KHz		0.004
	1MHz		0.011
Water Absorption	JIS K 6911 boil for 2hrs	wt%	0.1
Flame Resistance	UL-94		V-0 recognized

The above values are typical and not specification.



Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan
 TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan
 TEL : 81-463-86-8001 FAX : 81-463-86-8022