

Peltron®

Product Name	S-3048
Product Category	Conductive Adhesive
Use	Semiconductor Modules, Car Electro Devices, General Modules, Die Attach, Touch Panel, Solar Battery
Function	One Component Type

Item	Condition	Unit	Typical Value
General Item			
Package	–	–	Pot, Syringe
Liquid Feature			
Storage Stability	Unopen / Frozen (below -15°C)	–	3 months
Cured Properties			
Recommended Curing Condition	Heat air circulation oven	–	150°C x 60 minutes
Volume Resistivity	150°C x 60 minutes cure	Ω·cm	1.4 x 10 ⁻⁴
Characteristics	Tough coating strength Good coating crack resistance		

The above values are reference and not specification.



PELNOX, LTD.

Tokyo Sales Office 3-7-2, Nihonbashi-Honcho, Chuo-ku, Tokyo, 103-0023, Japan
TEL : 81-3-5645-3782 FAX : 81-3-5645-3784

R&D Center 8-7, Bodai, Hadano-shi, Kanagawa, 259-1302, Japan
TEL : 81-463-86-8001 FAX : 81-463-86-8022